



CLIENT: National Fireproofing Co.

Test Report No.: 23059-R1

Original Date: October 30, 2003

Revised Date: April 30, 2004

Note: This report supersedes the previous one bearing Report No. 23059 originally issued on 10/30/03.

SAMPLE SUBMITTED BY CLIENT AS: One (1) Fabric: Flamex PF 100% Polyester

DATE OF RECEIPT: October 29, 2003


TESTING PERIOD: October 30, 2003

TEST REQUESTED: Flame Propagation of Textiles and Films
NFPA std. 701/1999, Test Method 1


TEST RESULTS: Please refer to page 2

CONCLUSION: The submitted sample was found to meet the requirements of the above standard, when tested in it's original state only.

PREPARED BY:


Harshavardhan Chenna Narendra
Technician - Flammability
Textiles

SIGNED FOR AND ON BEHALF OF
SGS U.S. TESTING COMPANY, INC.


Ho Jun Park
Manager
Textile Laboratory

ts

Page 1 of 2

This report is issued by SGS U.S. Testing Company Inc. under its General Conditions for Testing Services, as printed on reverse side. SGS U.S. Testing's responsibility under this report is limited to proven negligence and will in no case be more than the amount of the testing fees. Except by special arrangement, samples are not retained by SGS U.S. Testing for more than 30 days. The results shown on this test report refer only to the sample(s) tested unless otherwise stated, under the conditions agreed upon. Anyone relying on this report should understand all of the details of the engagement. Neither the name, seals, marks nor insignia of SGS U.S. Testing may be used in any advertising or promotional materials without the prior written approval of SGS U.S. Testing. The test report cannot be reproduced, except in full, without prior written permission of SGS U.S. Testing Company Inc.



Report No.: 23059-R1
Original Date: 10/30/03
Revised Date: 4/30/04
Page: 2 of 2

CLIENT: National Fireproofing Co.

RESULTS:

Flame Propagation of Textiles and Films

National Fire Protection Association STD. 701/1999-Test Method 1

Conditioning: 220°F ± 5°F oven for 30 minutes

<u>Original wt.</u> (grams)	<u>Post wt.</u> (grams)	<u>After Flame</u> (seconds)	<u>Residues</u> (seconds)	<u>Wt. Loss</u> (percent)
9.0	6.3	0.0	0.0	30.0
9.2	6.3	0.0	0.0	31.5
9.4	6.1	0.0	0.0	35.1
9.2	5.9	0.0	0.0	35.9
9.0	5.7	0.0	0.0	36.7
9.3	6.3	0.0	0.0	32.3
9.7	5.8	0.0	0.0	40.2
8.8	5.6	0.0	0.0	36.4
9.6	6.3	0.0	0.0	34.4
8.8	5.3	0.0	0.0	39.8
		AVG	0.0	35.2
		3*STDEV		10.0
		AVG + 3STDEV		45.2

Requirements: Average weight loss shall not be more than 40% and any individual specimen shall not exceed the mean value plus three standard deviations.

Flaming Fragments

Or Residues: Shall not continue to flame after reaching the floor of the tester for more than an average of two seconds per specimen for the sample of 10 specimens.

End of Report